

## NEW Swift Optical Shutters





Polarized transmission of the Swift Optical Shutter in the open state



Swift LC Response Time Plot

					_
	ORDERING INFORMATION				
	Diameter, D (in.)	Clear Aperture,CA	Thickness t (in.)	Part Number	
	2.00	0.70	0.75	SCS - 200	

## meadowlark optics

© 2008 Meadowlark Optics, Inc. All rights reserved.

## **Key Benefits**

- No mechanical motion
- Computer control capability
- Noiseless
- High speed

This liquid crystal shutter is a vibration-free alternative to mechanical shutters for use in high-speed shutter applications. It uses a Swift LC cell between crossed polarizers to provide submillisecond switching for both opening and closing. Switching time is 125 microseconds to open and 125 microseconds to close. The switching times are less than 50 microseconds if the shutter is heated to 40° C. The D3060HV controller provides this temperature control capability. These shutters show some haziness in the liquid crystal layer in the blue and green wavelengths. The light loss from this haze is about 1% at 700 nm but increases monotonically to about 10% loss at 450 nm. Scatter at wavelengths above 700 nm is negligible. The shutter is supplied with integral dichroic visible polarizers that function over the wavelength range of 450 nm to 700 nm to provide an average contrast ratio of better than 200:1. Shutters with larger aperture sizes and with wavelength coverage to 2.1 microns are available on a custom basis. Please call with your special requirements.

SPECIFICATIONS			
Retarder Material	Polymer stabilized nematic		
	liquid crystals		
Substrate Material	Optical quality synthetic fused silica		
Polarizer Material	Dichroic Polymer		
Wavelength Range	450-700 nm		
Contrast Ratio (average)	200:1		
Angular Field of View	± 5° incidence angle		
Switching Time (10% to 90%) at re	oom temperature		
Closed to open:	125 μs		
Open to closed	125 μs		
Switching Time (10% to 90%) at	50 μs		
40° C			
Transmitted Wavefront	λ/2		
Distortion			
Surface Quality	60-40 scratch and dig		
Reflectance (per surface):	≤ 0.5% at normal incidence		
Beam Deviation	≤ 5 arc min		
Recommended Safe	1 W/cm², CW		
Operating Limit			
Glass Thickness	0.48 — 0.52 inches		
Polarization Direction	Vertical on input face, horizontal		
	on output face		
Storage temperature	-20° C to +70° C		
Operating temperature	-10° C to +60° C		

(303) 833-4333 (303) 833-4335 Fax

5964 Iris Parkway, PO Box 1000

Frederick, Colorado 80530 USA

mlo@meadowlark.com www.meadowlark.com